

## Kroko - Ostrich – Galuchat - exklusive Luxus

**Herkunft:** Europäische Rindshäute

**Stärke:** 1.0/1.2 mm

**Oberfläche:** geprägtes Rindsleder

Ein klassisches Rindnappa wird durch eine speziell entwickelte Technik mit dem typischen Krokodil-, Strauß- oder Rothenoptik geprägt. Der Artikel Galuchat leitet seinen Namen dem Franzosen Jean-Claude Galuchat der am Hof von Ludwig XV Luxus-Objekte in Rothenleder bekleidete.

## Kroko - Ostrich – Galuchat - Exclusieve luxe

**Oorsprong:** Europese rundshuiden

**Dikte:** 1.0/1.2 mm

**Bewerking:** geprent rondslede

Klassiek nappaleder wordt met een speciaal ontwikkelde techniek voorzien van de typische krokodil-, struisvogel- of roggenoptiek. Het artikel Galuchat ontleent zijn benaming aan de Fransman Jean-Claude Galuchat die aan het hof Van Lodewijk XV luxeobjecten in roggenleder bekleedde.

## Kroko - Ostrich – Galuchat - de Luxe exclusif

**Origine:** peaux bovines européennes

**Epaisseur:** 1.0/1.2 mm

**Traitemet:** cuir imprimé

A l'aide d'une technique spécialement conçue, un aspect croco, autruche ou galuchat est imprimé dans un cuir nappa. Le Galuchat tire son nom du Français Jean-Claude Galuchat qui à la cour de Louis XV recouvrait des objets de luxe en peau de raie.

## Kroko - Ostrich – Galuchat - exclusive luxury

**Origin:** european bovine hides

**Thickness:** 1.0/1.2 mm

**Treatment:** embossed cattlehide

With a special process, a croco-, ostrich- or raydesign is printed in a traditional nappaleather. The article Galuchat is named after the Frenchman Jean-Claude Galuchat who at the court of Louis XV covered luxury objects in ray.

### PHYSICAL TESTS

Requirements and standard reference	Test Method	Real Value
Dry rub fastness	EN ISO 11640	50 cycles value >= 3 grey scale
Wet rub fastness	EN ISO 11640	20 cycles value >= 3 grey scale
Sweat rub fastness	EN ISO 11640	50 cycles value >= 4 grey scale
Crack resistance	EN ISO 5402	30,000 - no damage
Light Fastness	ISO 105 - B02	>= 3 grey scale
Inflammability	DIN EN 1121-1 EUFAC (European upholstery union)	
<b>Environment</b>	The leathers are being produce ecologically safe, according to laws and regulations without AZO colours	
<b>PCP</b>	According to the PCP-regulation dated 12/12/1989	

Further parameters can be communicated upon request.